

IDEAL MEDICAL INDUSTRIES CO., LTD.

LUTIAN BASE, POYANG INDUSTRY ZONE, SHANG RAO, JIANGXI, CHINA

Tel:+86 574 27835985 Fax:+86 574 27835990

Ideal Sterile Latex Surgical Gloves Certificate of Analysis

Powdered

Product Name		Powdered Latex Surgical Gloves	Product Standard	EN455-1, -2-3	
Lot No.		20220210	Type, Size	6,6.5,7,7.5,8	
MFG Date		2022-02	EXP Date	2027-01	
Lot Quantity		500000 pairs	Sample Quantity	315 pairs	
Sampling		02-03-22~03-03-22	Test Date	03-03-22~10-03-22	
Sampler		Lixia Zhang	Identifier	Lixia Zhang	
Test Item		Index	Test Level	Test Result	Result
Before Aging	Tensile Strength	≥12 N	S-2 AQL 1.5	14.4~16.1, 0/13	Pass
Aged	Tensile Strength	≥9 N	S-2 AQL 1.5	13.2~14.5, 0/13	Pass
6#	Length	≥260 mm	S-2 AQL 1.5	266~274, 0/13	Pass
	Width	78±5mm	S-2 AQL 1.5	75~82, 0/13	Pass
	Thickness	≥0.10mm	S-2 AQL 1.5	0.28~0.31, 0/13	Pass
6.5#	Length	≥265 mm	S-2 AQL 1.5	268~273, 0/13	Pass
	Width	83±5mm	S-2 AQL 1.5	81~86, 0/13	Pass
	Thickness	≥0.10mm	S-2 AQL 1.5	0.28~0.31, 0/13	Pass
7#	Length	≥270 mm	S-2 AQL 1.5	273~277, 0/13	Pass
	Width	89±5mm	S-2 AQL 1.5	88~92, 0/13	Pass
	Thickness	≥0.10mm	S-2 AQL 1.5	0.28~0.31, 0/13	Pass
7.5#	Length	≥270 mm	S-2 AQL 1.5	275~280, 0/13	Pass
	Width	95±5mm	S-2 AQL 1.5	93~99, 0/13	Pass
	Thickness	≥0.10mm	S-2 AQL 1.5	0.28~0.31, 0/13	Pass
8#	Length	≥280 mm	S-2 AQL 1.5	280~283, 0/13	Pass
	Width	103±6mm	S-2 AQL 1.5	101~106, 0/13	Pass
	Thickness	≥0.10mm	S-2 AQL 1.5	0.28~0.31, 0/13	Pass
Leachable Protein		200µg/dm ²	3 pcs	80.0 µg/dm ²	Pass
Freedom from holes			G-1 AQL1.5	0/315	Pass
Labeling			S-2 AQL 1.5	0/13	Pass
sterilize result			N/A	A	Pass
Biological Test			Non-Irritation to Rabbit's Skin and Non-sensitization to Guinea Pig's Skin.		
Determinant Compliance			This lot conforms to the requirements established by the specifications of EN455-1, EN455-2 and EN455-3.		

Approved By: Xiaoling Hong/ QC Dept.

江西云鹤橡塑有限公司
IDEAL MEDICAL INDUSTRIES CO., LTD.
朱 轶 骥